

HI-FORZA 670

(Polycarboxylate Based Admixture For Conventional Self Consolidating Concrete In Precast Applications.)

DESCRIPTION

HI- FORZA 670 is a high-range water-reducing admixture for concrete. Its unique formulation is based upon the latest polycarboxylate ether polymers having the ability to disperse cement particles and result in flowability. HI- FORZA 670 does not contain calcium chloride or any other intentionally-added chlorides and will not contribute to corrosion of steel reinforcement present in the concrete.

USES

HI-FORZA 670 is recommended for use in:

- Concrete requiring high-early compressive strength development.
- Concrete where high flowability, increased stability and durability are needed.
- Producing self-consolidating concrete (SCC) mixtures.
- Concrete with varying water reduction requirements (5-40%).
- Applications requiring workability retention.

ADVANTAGES

- Low viscosity admixture suitable for pumping.
- Different grades of concrete to greater heights.
- Suitable for concrete having cement replacements and low water cement ratio.
- Provides higher strength without increase in cement content or reduction in workability.
- Ideal for precast concrete production.
- Reduces shrinkage cracking because of lower water cement ratio. Makes the concrete water impermeable.
- Increase Durability.
- Dosage flexibility.

SHELF LIFE

1 year in original, unopened container.

TECHNICAL DATA

Appearance	: Light to pale yellow
Form	: Liquid
Odor	: Odorless
Specific Gravity	: 1.07 To1.08 @ 20°C
pH Value	: Above 6
Chloride Content	: Nil

DIRECTIONS

Dosage: HI-FORZA 670 is an easy to dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of concrete performance requirements.

Addition rates for HI-FORZA 670 can vary with the type of application, but will normally range from 0.3 - 1.25% by weight of cementitious materials.

Should conditions require using more than the recommended addition rate, please consult your Hi-Bond representative.

Trial mixes should be run to verify plastic and hardened performance with local materials. Over dosage may cause delay in the setting time.

STORAGE

HI-FORZA 670 should be stored at temperatures above 5°C. If frozen, its properties can be recovered after thawing and agitating thoroughly.

SAFETY

During use, avoid contact with the skin and eyes. Wear protective gloves and eye protection when handling the product. In case of contact with the eyes rinse with plenty of fresh water and seek medical advice.

PACKING

HI-FORZA 670 is available in 225 kg HDPE Barrels

STANDARD COMPLIANCE

HI FORZA 670 complies with IS 9103 1999(2007)

This Product is Formulated and Labeled and Commercial use only

For Best Results and Safest Usage, User is Specialty Directed to Consult.

Product Warranty: All recommendations, statements and technical data contained herein are based on tests we believe to be reliable and correct, HI BOND warrants its products to be free of major defects and that, at the time and place of shipment, our material will meet current published physical properties when applied within HI BOND'S directions and tested in HI BOND'S standards. HI BOND'S facility is limited to replacement of material found to be defective. As HI BOND has no control over the use to which others may put its products. It is recommended that the product be tested to determine if suitable for a specific application and / or our information is valid in particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, applications and proper installation of each product. Nothing contained herein shall be construed to be a recommendation to use or as a license to operate under or to infringe any existing patents.